



<b>Product Code</b>	VIC-CHR-503277
<b>Description</b>	4-Hole Bath & Shower Mixer, Deck Mounted
<b>Flow Rate</b>	25.00 LPM @ 3 bar
<b>Recommended Water Pressure</b>	1.0 Bar - 5 Bar
<b>Material Composition Specification in Percentage</b>	<p><b>Brass Ingots as per IS:1264-1997</b> Cu (58.0-63.0), Sn (0.0-1.0), Pb (0.5-2.5), Ni (0.0-1.0), Al (0.2-0.8), Mn (0.0-0.5), Total Impurity (0.0-2.0), Zn (Remainder)</p> <p><b>Brass Rod as per IS:319-1989</b> Cu (56.0-59.0), Pb (2.0-3.5), Fe (0.0-0.35), Total Impurity (0.0-0.7), Zn (Remainder)</p> <p><b>Brass Pipe as per IS:407-1996</b> Cu (62.0-65.0), Pb (0.0-0.3), Fe (0.0-0.01), Total Impurity (0.0-0.6), Zn (Remainder)</p> <p><b>ABS:</b> Specific Gravity (g/cm<sup>2</sup>) 1.06-1.10, Melt Mass Flow Rate (g/10 min.) 20-26, Rockwell Hardness 95-115, DTUL @ 66 psi (0.45 MPa) (OC) 78-102</p>
<b>Cartridge Specification</b>	Life Cycle EN 200: 200,000 cycles (Standard) - 5.0 LAC Cycles as per EN 200*
<b>Water Tightness</b>	16 bar (Pass)
<b>Pressure Resistance</b>	25 bar (Pass)
<b>Finish</b>	Plating: Nickel-13.0 micron Chromium-0.40 micron Salt Spray (700 hrs + Validated) Adhesion (Pass)
<b>Available Colour Finishing</b>	Black Chrome (BCH), Black Matt (BLM), Gold Bright PVD (GBP) & Blush Gold Bright PVD (BGP)

\* As per in-house testing done on automatic life cycle testing machine made by Giussani, Italy

DISCLAIMER: Our every effort has been made to ensure factual accuracy, the information presented subject to changes due to requirements in different sites, markets and/ or countries. 10% variation in flow rate may be possible. Jaquar reserves the right to make the necessary amendments at any time without prior notice.